

Agropur Primer

2K-PUR-zinc phosphate primer



Product description

Description/Material	2-component anticorrosive primer.
Binding material / active substances	Based on polyurethane, contains zinc phosphate.
Purpose	For corrosion protection of steel.
Properties	Fast-drying, 2-component anticorrosive primer, free of lead and chromate. Overcoatable with 2-component PUR-coating materials, and also with 1-component coatings with greater dissolving capacity.
Colors	<ul style="list-style-type: none"> ■ Hellgrau (light grey) ■ Rotbraun (red brown) ■ Hellbeige (oatmeal)
Packaging / container sizes	<ul style="list-style-type: none"> ■ 4,75 kg (incl. component B). ■ 28,5 kg (incl. component B).
Storage	Storable in perfectly sealed original containers, dry and cool, for 18 months. Partial quantities of opened containers have to be used up fast.
Quality assurance	High quality products require strict control of raw materials and their processing. In-house chemists ensure this quality from receipt to exit of the goods. AvenariusAgro produces according to the TÜV-approved and certified quality management system ISO 9001-2015 and was awarded with the Responsible Care certificate.

Technical data

Consumption	<ul style="list-style-type: none"> ■ Theoretical: 0,19 kg/m² for 80 µm DFT. ■ Practical: approx. 0,28 kg/m² for 80 µm DFT.
Recommended film thickness	80 µm dry film thickness, equal to 125 µm wet film thickness.
Mixing ratio	<ul style="list-style-type: none"> ■ 18 parts by weight comp. A 1 part by weight comp. B ■ 11 parts by volume comp. A 1 parts by volume comp. B
Density	Approx. 1,5 kg/l.
Pot life	<ul style="list-style-type: none"> ■ At 10°C: approx. 5 hours. ■ At 20°C: approx. 3 hours. ■ At 30°C: approx. 2 hours.
Solids content	<ul style="list-style-type: none"> ■ By weight: approx. 77 %. ■ By volume: 63 % (DIN 53219).
Flash point	<ul style="list-style-type: none"> ■ Component A: 25 °C. ■ Component B: 38 °C. ■ Mixed material: 27 °C.
Drying	According to DIN 53150, for 80 µm dry film thickness, at 23 °C: <ul style="list-style-type: none"> ■ Degree of dryness 1: 45 minutes. ■ Degree of dryness 4: 2 hours. ■ Degree of dryness 6: 4 hours.
VOC	See safety data sheets.
Thinner	Verdünnung 65. For Brush- or Roller-application and at high ambient temperatures Verdünnung 80 should be used.

Resistance

Chemical	Good resistance against water, occasionally fumes of acid and caustic solutions, oils, fats and short term exposure to fuels.
Mechanical	Largely insensitive to knocks and very abrasion resistant.
Weather	Resistant to weather, high resistance against chalking and good color stability.
Temperature	Dry: up to 150°C.

Processing

Surface preparation	<ul style="list-style-type: none"> ■ Steel: The surface has to be dry and free of fat, oil, dirt and dust. Sandblasting Sa 2½ (EN ISO 8501-1). ■ Galvanized steel: The surface has to be dry and free of fat, oil, dirt and dust. Remove white rust (grinding or sweep-blasting), for outdoor areas sweep-blasting is necessary. ■ Aluminium: The surface has to be dry and free of fat, oil, dirt and dust. Grinding or sweep-blasting, for outdoor areas sweep-blasting is necessary.
Coating proposal	1 – 2 x Agropur Primer. Suitable top coats: all Agropur-products from our product range.
Material preparation	Stir up well component A. Then mix component A and B at specified mixing ratio. Mix only the quantity, which can be applied within the pot life.
Processing temperature	Do not work below +5°C and not above 80 % relative humidity, dew point distance at least 3°C.
Application	<ul style="list-style-type: none"> ■ Airless spray application. ■ Thinner: if required add max. 5 % Verdünnung 65.
Waiting periods	<ul style="list-style-type: none"> ■ Between priming coats: at least 4 hours (at 20°C / 50 % relative humidity). ■ Between priming and top coat: at least 4 hours (at 20°C / 50 % relative humidity). <p>Depending on temperature and drying-conditions. After longer waiting periods, the surface is recoatable after suitable surface preparation.</p>
Coating over old coats	Old Epoxy- or Polyurethane-coatings: grinding or sweep-blasting, free of dust. When in doubt, coating a test area is recommended.
Cleaning tools	Verdünnung 65 (Thinner 65) or Verdünnung 80 (Thinner 80). If not in continuous use, clean tools within the pot life.

Regulation governing chemicals

Disposal	Special waste incineration or problematic waste collection points. Do not dispose of together with household waste. Do not allow to enter drainage systems, the soil or water courses. Dispose soiled packaging in the same way as the product itself.
Safety Data Sheet	The safety Data Sheet may be accessed at http://www.avenariusagro.at

Technical Information: Agropur Primer, status: 10 / 2016

These technical data were compiled based on state of the art technology and our experience. Due to the many different substrates and conditions of the coated objects, we accept no liability for the technical information provided. The information therefore does not release the buyer / user from his responsibility to professionally test our materials for suitability for his envisaged application, under his pertinent conditions. The validity of this data sheet shall expire following the release of a revised / new PDF version.

Technical advice

Addressing all substrates found in practice and the treatment required when applying this product is beyond the scope of this data sheet. Our technical advisers will gladly assist you with additional detailed information relevant to your specific project.

Avenarius-Agro GmbH

Head office & factory: Industriestraße 51, A-4600 Wels, Telefon: +43/7242/4890, Telefax: +43/7242/489-5700, Internet: www.avenariusagro.at, E-Mail: office@avenariusagro.at
Vienna branch: A-1110 Wien, Sofie-Lazarsfeld-Str. 10, Tel.: 01 / 201 463 072, Fax: 01 / 201 46 - 3075, E-Mail: wien@avenariusagro.at